

Cemseal E100WB

Water Based Epoxy Coating System

cemseal[®]
Your Construction Chemical Partner

The Product

Cemseal E100WB is a water based, epoxy resin base industrial floor and wall coating system. It consists of modified epoxy resin and pigments. It is designed specially for thin layer coating and provides a matt / semi-glossy finish. It makes the industrial floors dust-free, easily cleanable, seamless and good abrasion resistance. It is available in a wide range of attractive colours.

Uses

- » New / old factory wall / floors
- » Warehouse wall / floors
- » Re-surfacing of factory wall / floors
- » Primary used in floor surfaces subjected to light traffic exposure and mechanical abuse
- » Other industrial sectors where a clean working environment is required

Advantages

- » Good resistance against light and foot traffic
- » Seamless and monolithic application
- » Economical to use due to its easiness and time saving
- » Good workability for easy and fast application
- » Prepackaged for accurate on-site mixing

Technical & Physical Data

Colour	Component A	: Liquid / Standard colour chart
	Component B	: Liquid / Clear
	Component A + B	: See separate colour chart
Packaging	Component A + B	: 5, 25 kg/set
Coverage		10 m ² / coat / kg
Pot Life at 25°C		30 minutes
Curing Time at 25°C	Foot Traffic	: 24 hours
	Fully Cured	: After 7 days
Thinner / Cleaner		Clean water
Shelf Life		12 months of kept in a cool dry sheltered place

Cemseal Industries Sdn Bhd
(Co. No.884153-T)
9 & 11, Jalan Besi,
Taman Sri Putri,
81300 Skudai, Johor,
West Malaysia

T +607-558 3320

F +607-556 9127

E info@cemseal.com.my

Method of Statement

Substrate Preparation	<p>NEW CONCRETE : The surface must be firm, dry, clean, free of dirt, oil, grease and all other foreign matter. A minimum tensile strength of 200 psi is required of the prepared surface before coating. Mechanical methods such as sandblasting, scarifying or shot blasting should be carried out to remove the weak layer of surface laitance. Acid etching is possible but less desirable. Care must be taken to ensure all residue acid must be removed with clean water before priming.</p> <p>EXISTING CONCRETE : The surface must be existing structurally sound, dry and free of all contaminants. Weak or contaminated concrete must be removed until sound concrete is realized. Old coatings, toppings, waxes, oils etc. must be removed by mechanical methods or acid etching before priming. Acid etching is possible but less desirable.</p>
Mixing	First pour the liquid Component A into a suitable container and stir with a slow speed paddle stirrer. Slowly, add Component B until a consistent colour is achieved.
Application	Apply the mixed Cemseal E100WB compound onto the prepared floor and an intermittent period of 8 hours should be allowed prior to the subsequent coats. Cemseal E100WB epoxy resin coating can be applied either by roller, airless sprayer or brush.
Limitation	The application of Cemseal E100WB is not possible at below 15°C and on frozen surface.

For Further Information	Cemseal Industries Sdn Bhd (Company No. 884153-T) No. 9 & 11, Jalan Besi, Taman Sri Putri, 81300 Skudai, Johor, West Malaysia. Tel : 607-558 3320, Fax : 607-556 9127, E-mail : info@cemseal.com.my
First Aid	In case of contact with eyes, skin or body wash immediately with clean fresh water or stand under shower and wash off. In case of inhaling of vapor or ingestion remove to fresh air and do not induce vomiting. Obtain immediate medical treatment.
Statement of Responsibility	The technical information and application advice given in this Cemseal publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature no assumption can be made as to a products suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user, is responsible for checking the suitability of products for their intended use.
Note	Field service where provided, does not constitute supervisory responsibility. Suggestions made by Cemseal either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Cemseal are responsible for carrying out procedures appropriate to a specific application.