## **Cemseal Grout GP**

Multi Purpose Non-Shrink Cementitious Grout



The Product	Cemseal Grout GP is a multi-purpose non-shrink cementitious grout. Cemseal Grout GP is based on Portland cement, graded aggregate and chemical additives, which impart controlled expansion whilst in the plastic state.
Uses	<ul> <li>Cemseal Grout GP is suitable for repair the following concrete structures:</li> <li>General purpose grouting</li> <li>Machine Foundations</li> <li>Columns in precast Construction</li> <li>Fill core holes, rod holes and defects in concrete</li> <li>Precast and prestressed panels</li> <li>Caulking of joints and pipes</li> <li>Honeycombs</li> </ul>
Advantages	<ul> <li>Cemseal Grout GP is an economical and easy application material requiring the simple addition of water. Other beneficial properties :</li> <li>Ready to use, premixed, requires only the addition of water.</li> <li>Can be dry packed, rammed, trowelled, poured and pumped.</li> <li>Good pumping properties</li> <li>No metallic iron content to cause staining.</li> <li>Low permeability</li> <li>Non- toxic</li> </ul>
Technical & Physical Data	
Form	Premixed Powder
Colour	Grey
Packaging	25 kg / bag
	Pourable Flowable
Compressive Strength	
(Tests at Temperatures 25°C	

(Tests at Temperatures 25°C)		
1 day	30 N/mm <sup>2</sup>	25 N/mm <sup>2</sup>
3 days	55 N/mm <sup>2</sup>	45 N/mm <sup>2</sup>
7 days	65 N/mm <sup>2</sup>	55 N/mm <sup>2</sup>
28 days	75 N/mm <sup>2</sup>	60 N/mm <sup>2</sup>
Mix Designs per 25 kg	3.8 litres	4.3 litres
Bags required per m <sup>3</sup>	76 bag	74 bag
Initial Setting Time	> 5.00 hrs	
Expansion	0.60% ~ 2.00%	
Bleeding	0.00%	
Shelf Life	12 months of kept in a cool dry sheltered place	

## **Cemseal Industries Sdn Bhd**

(Co. No.884153-T) 9 & 11, Jalan Besi, Taman Sri Putri, 81300 Skudai, Johor, West Malaysia

T +607-558 3320 F +607-556 9127 E info@cemseal.com.my

## Method of Statement

Surface Preparation	* *	The substrate must be clean, sound and free from oil, grease, laitance, curing compound or any loosely adhering particles. Weak or contaminated concrete must be removed until sound concrete is realized. Metal (steel & iron) surfaces and bolts or anchor holes must be clean and free from scale, rust, oil, grease, dust or loose material.
Application	• •	The concrete substrate should be pre-soak prior to application of Cemseal Grout GP. To pre-soak the substrate with clean water for a minimum of 5 hours prior to the grouting. Before application, the excess water should be removed & all water in the anchor and bolt holes must be blown out and no trace of free water present whilst the grouting process. It is essential that the formwork be constructed to facilitate rapid continuous and complete filling at area to be grouted. The formwork constructed had to be leak proof and watertight. Place about 75% of the premeasured clean water (depending on consistency required) into a clean container and gradually add the whole bag of Cemseal Grout GP into it while continuously mixing. Slowly add Cemseal Grout GP powder whilst mixing. Add the remaining water until the desired consistency is obtained. The mixing must be continued for a maximum of 3 minutes until a homogenous consistency is obtained. For optimum results Cemseal Grout GP must be mixed with a slow speed drill (Maximum 500rpm). Cemseal Grout GP can be placed in thickness ranging from 20mm to 120mm in one single application. Where thickness is greater than 50mm, it is necessary to fill Cemseal Grout GP with graded 10mm silt free aggregates to minimise temperature rise generated during the curing stage. The quantity of aggregates should not exceed 1 part aggregates to 1 part Cemseal Grout GP by weight. It is recommended that a suitable head box be used to ensure continuous flow of grout. Ensure entire area to be grouted is filled by bringing level to above underside of machine base and remain at this level throughout grout placement. The grout head must be maintained at all times so that a continuous grout front is achieved. Do not use machine vibrators to assist in flow, as this will cause segregation of grout. For large areas it is recommended that Cemseal Grout GP may be pumped using heavy duty diaphragm pumps.
Curing	•	If formwork type repair is used, leave the formwork in place for at least 3 days. Upon removal of the formwork, cure the exposed surface immediately with curing compound or use other approved curing methods.
Others Application	То	consult the local Cemseal's representative.

For Further	Cemseal Industries Sdn Bhd (Company No. 884153-T)				
Information	No. 9 & 11, Jalan Besi, Taman Sri Putri, 81300 Skudai, Johor, West Malaysia. Tel : 607-558 3320, Fax : 607-556 9127, E-mail : info@cemseal.com.my				
First Aid	In case of contact with eyes, skin or body wash immediately with clean fresh water or stand under shower and wash off. In case of inhaling of vapor or ingestion				
	remove to fresh air and do not induce vomiting. Obtain immediate medical treatment.				
Statement of	The technical information and application advice given in this Cemseal publication are based on the present state of our best scientific and practical knowledge.				
Responsibility	As the information herein is of a general nature no assumption can be made as to a products suitability for a particular use or application and no warranty as to its				
	accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user, is responsible for checking the suitability of				
	products for their intended use.				
Note	Field service where provided, does not constitute supervisory responsibility. Suggestions made by Cemseal either orally or in writing may be followed, modified				
	or rejected by the owner, engineer or contractor since they, and not Cemseal are responsible for carrying out procedures appropriate to a specific application.				